

## Chemical resistant rubber

ISO	CSM Chlorosulphonated Polyethylene
Shape	Rolls
Color	Black
Temperature Range	-30 and 120 °C
Density	1500 kg/m <sup>3</sup>
Hardness	70 Shore A (± 5)
Elongation at break	300 %
Tensile strength	8 N/mm <sup>2</sup>

## Material information

Measurement tolerance 7715-P3

Weather-resistant high-density rubber. Suitable for applications with acids and alkalis and salt water. Good chemical resistance.

Petrol	Oil	UV	Acids	Alkali
Low	Good	Good	Excellent	Excellent

## Item Overview

Item Code	Item Name	Width (mm)	Length (mm)
12500030	CSM Hypalon 3 mm		
12500040	CSM Hypalon 4 mm		
12500050	CSM Hypalon 5 mm		

## Storage advice (ISO 2230)

The enclosed specification gives an indication of the storage periods to prevent degradation in properties of the material. Exposure to light and moisture should be avoided as much as possible. It is advisable to check the material in advance if it is to be stored for more than one year.

Group	Minimum temperature	Maximum temperature	Maximum humidity	Shelf life	Extension after inspection
C	10 °C	25 °C	65 %	10 year	5 year

We provide product information as known by us with great care. We cannot accept any liability for errors and/or inaccuracies and/or incompleteness. Please note that our products are intended for professional use only. For high impact applications and/or combinations of limit values we always recommend to have the properties specific to that situation verified by us. If there are multiple specifications for a product we will use the standard of 2mm or the closest specification.

