

SBR met een doekafdruk.



ISO	SBR Styreen-Butadien Rubber
Shape	Rolls
Color	Black
Temperature Range	-10 and 70 °C
Density	1460 kg/m3
Hardness	70 Shore A (± 5)
Elongation at break	200 %
Tensile strength	4 N/mm2

Material information

SBR with a cloth imprint on one side of the material for effective bonding or limited non-slip applications.

Usage examples

Seals and underlay strips for shipbuilding and general industry.
Measurement tolerance 7715-P3

Petrol	Oil	UV	Water	Drinking water	Wear resistance	Acids	Alkali	Base
Not suitable	Not suitable	Not suitable	Not suitable	Not suitable	Not suitable	Not suitable	Not suitable	Not suitable

Item Overview

Item Code	Item Name	Width (mm)	Length (mm)
20501015	SBR doekafdruk met inlage 1,5+1 mm		
20501020	SBR doekafdruk met inlage 2+1 mm	1.400	20.000
20501030	SBR doekafdruk met inlage 3+1 mm	1.400	10.000
20501040	SBR doekafdruk met inlage 4+1 mm	1.400	10.000
20501050	SBR doekafdruk met inlage 5+1 mm	1.400	10.000
20502030	SBR doekafdruk met inlage 3+2 mm		
20502040	SBR doekafdruk met inlage 4+2 mm		
20502050	SBR doekafdruk met inlage 5+2 mm		
20502060	SBR doekafdruk met inlage 6+2 mm		
20502080	SBR doekafdruk met inlage 8+2 mm		

Compression set

[tbl_compressieset_explainer](#)

Testing Regulation	Duration	Temperature	Difference
ISO 815	22 hour(s)	70 °C	50 %



Storage advice (ISO 2230)

The enclosed specification gives an indication of the storage periods to prevent degradation in properties of the material. Exposure to light and moisture should be avoided as much as possible. It is advisable to check the material in advance if it is to be stored for more than one year.

Group	Minimum temperature	Maximum temperature	Maximum humidity	Shelf life	Extension after inspection
A	10 °C	25 °C	65 %	5 year	2 year

We provide product information as known by us with great care. We cannot accept any liability for errors and/or inaccuracies and/or incompleteness. Please note that our products are intended for professional use only. For high impact applications and/or combinations of limit values we always recommend to have the properties specific to that situation verified by us. If there are multiple specifications for a product we will use the standard of 2mm or the closest specification.

